

First edition
2011-11-01

**Nanotechnologies — Determination of
elemental impurities in samples of carbon
nanotubes using inductively coupled
plasma mass spectrometry**

*Nanotechnologies — Dosage des impuretés dans les nanotubes en
carbone (CNTs) par spectroscopie de masse à plasma induit (ICP-MS)*



Reference number
ISO/TS 13278:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 13278 was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

Introduction

Inductively coupled plasma mass spectrometry (ICP-MS) is a well-established multi-element analytical technique used for fast, precise and accurate determinations of trace elements. ICP-MS has many advantages over other elemental analysis techniques such as atomic absorption and ICP atomic emission spectrometry (ICP-AES). The ability to handle both simple and complex matrices with a minimum of matrix interferences is due to the high temperature of the ICP source. ICP-MS also has high sensitivity and superior detection capability.

Owing to their unusual physical and chemical properties, and potential applications in a number of areas, interest in carbon nanotubes (CNTs) has shown tremendous growth in the past decade. Metal particle catalysts are essential in the mass production of nanotubes by chemical vapour deposition (CVD)^{[1][2][3]}. Removal of these residual catalysts (typically Fe, Co, and/or Ni) after CNT production is one of the key challenges for the application of CNTs in many fields^[4]. After complicated purification steps, the concentration of such catalysts is measured. It is of great concern that the results of toxicological and ecological impact studies of carbon nanotubes could be misinterpreted due to the presence of impurities in the test materials^{[5][6][7]} and that the metals could be released into the environment during disposal of the product by means of combustion or other ways. Additionally, the actual desired performance of nanotube materials might depend on these impurities, which is the reason why it is so crucial to use reliable techniques to determine their content in these materials.

Currently available methods for analysis of the purity of CNTs include neutron activation analysis (NAA), transmission electron microscopy (TEM) with electron energy loss spectroscopy (EELS), scanning electron microscopy (SEM) with energy dispersive X-ray analysis (EDX), Raman spectroscopy, X-ray photoelectron spectroscopy (XPS), thermogravimetric analysis (TGA), and X-ray fluorescence (XRF) spectrometry^{[8][9][10][11][12]}. A number of these techniques for the characterization of single-wall and/or multiwall carbon nanotubes are the subject of standardization within ISO/TC 229, including SEM (ISO/TS 10798), TEM (ISO/TS 10797¹⁾), and measurement methods for the characterization of multiwall carbon nanotubes (ISO/TR 10929²⁾).

However, each method has its limitations for determination of elemental impurities. TGA can only provide a gross estimation of metal content. NAA is a quantitative and qualitative method based on nuclear reactions between neutrons and target nuclei. This method provides high efficiency for the precise and simultaneous determination of a number of major, minor and trace elements in different types of samples in the parts per billion (10^{-9}) to parts per million (10^{-6}) range. Moreover, due to the superior figures of merit, including high accuracy, good precision and no matrix blank requirement, NAA is widely used in the certification of reference materials. NAA is, however, not a technique that is readily available, being not only a highly specialised field of analysis, but also requiring access to a nuclear reactor. ICP-MS, on the other hand, is also capable of providing highly accurate and precise results, while being widely available in most commercial laboratories. However, using conventional solution sample introduction ICP-MS, the sample has to be completely solubilised. Digestion of some types of samples requires thorough pretreatment schemes. Standard sample preparation procedures are available for routine matrix types, including soils, rocks and biological specimens. In the case of carbon nanotubes, because of their extremely stable structure and possible encapsulation of metals in structural defects, it is necessary that the materials go through special destructive pretreatments before analysis by ICP-MS^{[12][13][14][15]}. ICP-MS offers better sensitivity than graphite furnace atomic absorption spectrometry with the multi-element speed of ICP-AES.

The purpose of this Technical Specification is to provide guidelines for optimized sample pretreatment methods for single-wall carbon nanotubes (SWCNTs) and multiwall carbon nanotubes (MWCNTs) to enable accurate and quantitative determinations of elemental impurities using ICP-MS. An example of the determination of elemental impurities in commercially produced carbon nanotubes, using the methods described, is given in Annex A.

1) Under preparation.

2) Under preparation.

Nanotechnologies — Determination of elemental impurities in samples of carbon nanotubes using inductively coupled plasma mass spectrometry

1 Scope

This Technical Specification provides methods for the determination of residual elements other than carbon in samples of single-wall carbon nanotubes (SWCNTs) and multiwall carbon nanotubes (MWCNTs) using inductively coupled plasma mass spectrometry (ICP-MS).

The purpose of this Technical Specification is to provide optimized digestion and preparation procedures for SWCNT and MWCNT samples in order to enable accurate and quantitative determinations of elemental impurities using ICP-MS.

2 Normative reference

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-3, *Nanotechnologies — Vocabulary — Part 3: Carbon nano-objects*