

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

| | |
|-----------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------|
| IEC 60216-2 Edition 4.0 2005-08 | IEC 60216-2 Édition 4.0 2005-08 |
| ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES – | MATÉRIAUX ISOLANTS ÉLECTRIQUES – PROPRIÉTÉS D'ENDURANCE THERMIQUE – |
| Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria | Partie 2: Détermination des propriétés d'endurance thermique de matériaux isolants électriques – Choix de critères d'essai |

CORRIGENDUM 1

Corrections to the French version appear after the English text.

Les corrections à la version française sont données après le texte anglais.

Table 1 – Examples of insulating materials, with recommended test properties and end-points

Replace, in Table 1, the row "Resin based reactive compounds (embedding compounds, potting compounds, encapsulating compounds)" with the following:

| 1 | | 2 | 3 | 4 | | | 5 |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|----------------------------------------|------------------------|-----------|---------------|---------|-----------------------------|
| Insulating materials | | Material specification Publication No. | Recommended properties | Preferred | Subsidiary 5) | Type 1) | Test method Publication No. |
| Resin based reactive compounds (embedding compounds, potting compounds, encapsulating compounds) Unfilled epoxy resinous compounds Filled epoxy resinous compounds Unfilled polyurethane compounds Filled polyurethane compounds | | IEC 60455 | Flexural strength | 50 % | | R | ISO 178 |
| | | | Loss of mass | 10 % | 3 %; 5 % | L | |
| | | IEC 60455 | Loss of mass | 3 % | 5 %; 10 % | R | ISO 178 |
| | | IEC 60455 | Flexural strength | 50 % | | | |

Corrections à la version française:

Cette correction ne s'applique qu'à la version anglaise.